

Journal of Pharmaceutical Research International

33(60B): 3702-3710, 2021; Article no.JPRI.78314 ISSN: 2456-9119 (Past name: British Journal of Pharmaceutical Research, Past ISSN: 2231-2919, NLM ID: 101631759)

Antimicrobial Activity of Zinc Oxide Nanoparticles Synthesized Using Leaves Extract of *Abies webbiana*

R. Nivethitha ^a, M. Jeevitha ^{b*}, S. Rajeshkumar ^c and Selvaraj Jayaraman ^d

 ^a Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai, India.
^b Department of Periodontics, Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai, India.

^c Department of Pharmacology, Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai, India.

^d Department of Biochemistry, Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai, India.

Authors' contributions

This work was carried out in collaboration among all authors. Author RN designed the study, performed the statistical analysis, wrote the protocol and wrote the first draft manuscript. Authors MJ and SR managed the analyses of the study. Author SJ managed the literature searches. All authors read and approved the final manuscript.

Article Information

DOI: 10.9734/JPRI/2021/v33i60B35065

Open Peer Review History:

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: https://www.sdiarticle5.com/review-history/78314

> Received 22 October 2021 Accepted 27 December 2021 Published 28 December 2021

Original Research Article

ABSTRACT

Introduction: Green synthesis of nanoparticles using plant extract, bacteria, fungi and enzymes are eco-friendly and cost effective which do need high pressure, energy, temperature and toxic chemicals for its synthesis protocol. Zinc oxide nanoparticles have various physical, chemical and biological properties which can be applied in the treatment of oral diseases.

Aim: The main objective of the current study was to synthesize the zinc oxide nanoparticles (ZnO NPs) in a cost effective biological method. The extract of *A. webbiana* was used to synthesis Zinc oxide nanoparticles.

Materials and Methods: In this report, we used the extract of *A. webbiana* to synthesize zinc oxide nanoparticles and were characterized using U-V visible spectrophotometer and were tested for their antimicrobial activity against oral pathogens.

^{*}Corresponding author: E-mail: jeevitham.sdc@saveetha.com;

Nivethitha et al.; JPRI, 33(60B): 3702-3710, 2021; Article no.JPRI.78314

Results: These biosynthesized zinc oxide nanoparticles exhibited potent antimicrobial activity against oral pathogens, *Streptococcus mutans, Staphylococcus aureus and Enterococcus faecalis, Candida albicans* and can be developed as a novel medicine against pathogenic oral diseases. *Abies webbiana* extract mediated zinc oxide nanoparticles showed effective antimicrobial activity comparable to others.

Conclusion: With increasing demand in advancements in diagnosis and treatment modalities, green synthesis of zinc oxide nanoparticles using *A. webbiana which was found to have* potent antimicrobial action has wider applications in dentistry. This formulation needs to be further purified to isolate the component in the extract that makes it effective to be used in large scale production for targeted drug delivery against a wide array of oral microbial infections.

Keywords: Abies webbiana; antimicrobial activity; innovative technology; green synthesis; zinc oxide nanoparticles.

1. INTRODUCTION

Nanoparticles (NPs) are small estimated particles with improved synergist reactivity, warm conductivity, non-straight optical execution, and compound relentlessness due to their enormous surface territory to volume proportion [1,2]. NPs have begun being considered as nano antibiotics in light of their antimicrobial activities [3,4]. Nanoparticles have been included into a variety of modern health, nutrition, feed, space, chemical. and cosmetic care aoods. necessitating a green and environmentally friendly approach to their synthesis [5.6]. The properties of metallic nanoparticles, for example, gold, silver, iron and zinc nanoparticles have developed interests in biomedical applications [7].

Zinc oxide is а unique material with semiconducting, piezoelectric, and pyroelectric capabilities that has a wide range of applications in transparent electronics. UV light matters. piezoelectric devices, compound sensors, spin electronics. individual consideration items, coatings, and paints [8]. Biosynthesis of Zinc oxide nanoparticles (ZnO NPS) from plants like Aloe vera, Borassus flabellifer fruit, Sargassum muticum, Eichhornia crassipes, and furthermore from some bacterial and contagious species like Bacillus subtilis and Escherichia coli, Ureolytic microorganisms, Lactobacillus plantarum have been reported [9]. The plants are sometimes described as biosynthetic laboratories where different secondary metabolites are produced and stored. Secondary metabolites are organic compounds such as alkaloids, amino acids, carbohydrates, fixed oils, flavonoids, glycosides, gums, resins, saponins, sugars, tannins, volatile oil etc., which are responsible for their medicinal properties. There are a large number of traditionally used plants on earth having a wide range of medicinal efficacies [10,11].

Talispatra in Bengali and Hindi, Talispatram in Sanskrit, and Indian Silver Fir in English are all names for Abies webbiana Lindl. (Pinaceae), a huge tall evergreen tree indigenous to the Himalayan region [12,13]. The leaves of this plant have been traditionally used for their carminative, stomachic, expectorant, decongestant. antiseptic, astringent, antihyperglycemic, female antifertility, febrifuge and antispasmodic properties. Characteristics antibacterial. include astringent. antihyperglycemic, female fertility, febrifuge, and antispasmodic. Cough, phthisis, asthma, chronic bronchitis, and other pulmonary infections can be treated with decoctions of the leaves taken orally. Furthermore, leaves of the plant have been used traditionally for its chemotherapeutic efficacies in several ailments like hoarseness, chronic bronchitis, rheumatism, and other pulmonary affections [14,15]. Previously it has been reported the extracts from the leaves of the plants have antibacterial, mast cell stabilizing, anxiolytic, anti-tumour, anti-inflammatory, antitussive and CNS depressant actions. Our team has extensive knowledge and research experience that has translated into high quality publications [16-35]. The present study aim to synthesize, characterize and check antimicrobial activity of zinc oxide nanoparticles synthesized using leaves extract of A. webbiana.

2. MATERIALS AND METHODS

2.1 Study Organisms

The test organisms used in this study were obtained from the culture collections of the Nanomedicine Laboratory, Saveetha Dental College, Chennai. The organisms used in this study were *Streptococcus mutans, Staphylococcus aureus and Enterococcus faecalis, Candida albicans.*

2.2 Biosynthesis of Zinc Oxide Nanoparticles (ZnO NPs) Using *A. webbiana* Leaf Extract

1g of *A. webbiana* mixed with 100 mL of distilled water and boiled in 60-70 degree celsius in the heating mantle for 10-15 minutes and filtered using Whattman no 1 filter paper. 20 milli molar (0.574g) of Zinc sulphate was dissolved in 60 mL of distilled water. 40 mL of filtered *A. webbiana* extract is mixed with 60 mL of metal solution to obtain ZnO NPs.

2.3 Characterization of ZnO NPs

The optical properties of the synthesis of ZnO NPs were determined using UV - Vis spectroscopy wavelengths ranging from 250 to 650 nm. They were measured at different time periods.to determine the synthesis of ZnO NPs.

2.4 Antimicrobial Activity of Zinc Oxide Nanoparticles

The ZnO nanoparticles synthesized using A. webbiana were tested for antimicrobial activity by agar well diffusion method against pathogenic organisms namely S. aureus, E.faecalis, S. mutans, C. albicans. The pure culture of the bacterium was subcultured on Mueller Hinton agar. Wells of 9 mm diameter were made on Muller Hinton agar plates using gel puncture and each strain was uniformly swabbed onto the individual plates using sterile cotton swabs. Using a sterile micropipette, a standard antibacterial agent was loaded into one well and three different concentrations of zinc oxide nanoparticles sample solutions (25 µl, 50 µl and 100 µl) were poured into three other wells on all plates. The isolates of C. albicans were subcultured onto Rose Bengal agar. A standard antifungal disc (voriconazole) was placed on the agar plate and then nanoparticle sample solutions (25 µl, 50 µl and 100 µl) were poured onto three other wells on the plate. After incubation at 37°C for 24 hours, the different levels of the zone of inhibition of bacteria were observed and measured.

2.4.1 Measurement of zone of inhibition

The test plates were held in front of a desk lamp, and the zones were measured with a ruler held against the back of the petri plate. The diameters of the zones of inhibited growth were measured to the nearest whole millimeter.

3. RESULTS AND DISCUSSION

3.1 Visual Identification

The present study showed the synthesis of ZnO NPs by using A. webbiana. The colour changes the reaction mixture was observed in continuously at various periods of incubation. The zinc oxide was reduced into ZnO nanoparticles that are visually identified by colour changes (Fig. 1). The colour of the solution was changed to light brown at 1 h incubation time. The color was changed to dark brown after 24 h of incubation. There was no color change observed after 24 h which indicated that the ZnO NPs synthesis process was completed. According to several investigations, after one hour of incubation at room temperature with Zn nitrate, the colour of the leaf extract changed from light yellow to pale brown. The appearance of nanoparticles is indicated by a change in colour [36].



Fig. 1. Reduction of Zinc oxide ions to ZnO nanoparticles visually identified by colour changes at various periods of incubation time

3.2 UV Vis Spectrophotometer Analysis

UV - vis spectroscopy analysis depends on the arising of colour in the reaction due to excitation of the surface plasmon resonance band in a reaction mixture. Fig. 2 shows the UV absorption spectra of the synthesized ZnO NPs. The spectrum clearly shows that the absorbance steadily decreased with decrease in incubation time. The plasmon resonance band for ZnO NPs synthesized using *A. webbiana* showed high absorption at 370 nm. UV spectroscopy research revealed maximal absorption at around 330 nm in several experiments. A particle size analyser

was used to determine the particle size. The diameter of the particles was discovered to be 853 nm. When compared to a particle size analyzer, SEM characterizations of produced Zn nanoparticles reveal a substantially smaller diameter. Various magnifications were used to analyse the nanoparticles. Individual zinc particles as well as a number of aggregates were seen in the SEM picture. The antibacterial activity of the produced Zn nanoparticles was demonstrated against Gram positive and Gram negative bacteria, as well as a fungal strain [37].

3.3 Antimicrobial Activity of Zinc Oxide Nanoparticles against Oral Pathogens

The antimicrobial activity of ZnO NPs of A. webbiana assayed by a well diffusion method against oral pathogens showed minimum concentrations inhibitorv different at concentrations. In Table 1, it shows the inhibition of bacterial growth in various concentrations of biosynthesized ZnO NPs of A. webbiana. The antimicrobial activity of ZnO NPs synthesized using A. webbiana was evaluated according to their zone of inhibition and the results were compared with the activity of the standard antimicrobial agent. The antibacterial activity of ZnO NPs against gram positive S. aureus showed a zone of inhibition of 15.03 ± 0.23 mm

at the concentration of 100 μ l. The antimicrobial activity was high against *S. mutans* and *E. faecalis* at concentrations of 100 μ l. These results indicate the ZnO NPs of *A. webbiana* were assuring as an antibacterial activity against the pathogens employed [38].

Some researchers have reported that ZnO NPs disrupt bacterial cell membrane integrity, reduce cell surface hydrophobicity, and downregulate the transcription of oxidative stress-resistance genes in bacteria which leads to its lysis. Raieshkumar et al. reported that the positively charged AgNPs accumulate on negatively charged bacterial cell membranes to bring about structural alteration in cell membranes. Various mechanisms contribute to its antimicrobial activity such as generation of reactive oxygen species and bacterial protein denaturation [39]. Studies have also revealed that Zinc Oxide nanoparticles, clove and cinnamon have antiinflammatory and antioxidant properties. Zinc Oxide nanoparticles are known to have antiinflammatory properties by blocking proinflammatory cytokines, inhibiting mast cell proliferation and suppressing LPS induced COX-2 expression. Antioxidant Zinc Oxide nanoparticles are due to release of hydrogen which reduces DPPH free radical easily [40, 41].




Fig. 2. UV Spectroscopic analyses of Zinc oxide nanoparticles synthesized from the leaf extract of *A. webbiana* recorded as function of time

Anti-bacterial activity of mouthwash incorporated with silica nanoparticles was assessed against oral pathogens. Silica nanoparticles were synthesized using the sol-gel method. In sol-gel reaction, there is hydrolysis and condensation of Tetra-ethoxy silane, where it was first hydrolyzed to silicic acid, followed by a condensation reaction leading to the formation of Si-O-Si bonds. Silica nanoparticles incorporated in mouthwash showed a good potential as an antimicrobial agent that maintains control of biofilm, preventing initial colonization of bacteria [42].

Thus biologically synthesis nanoparticles have various biomedical applications owing to its antimicrobial, anti inflammatory, antioxidants properties [43–51.





Fig. 3. Antimicrobial activity of *Abies webbiana* mediated zinc oxide nanoparticles against oral pathogens





Oral Pathogens	Zone of inhibition (mm)			
	25 µL	50 µL	100 µL	Ab
S. aureus	12.24 ± 0.32	14.14 ± 0.31	15.03 ± 0.23	25.14 ± 0.23
S. mutans	18.03 ± 0.22	20.15 ± 0.23	25.15 ± 0.32	25.15 ± 0.32
E. faecalis	35.15 ± 0.24	37.04 ± 0.34	38.02 ± 0.24	38.23 ± 0.24
C. albicans	9.24 ± 0.12	9.12 ± 0.23	9.12 ± 0.32	40.32 ± 0.23

Table 1. Antimicrobial activity of ZnO NPs against oral pathogens

Table 1 shows the inhibition of bacterial growth in various concentrations of biosynthesized ZnO NPs of *A. webbiana*. The antimicrobial activity of ZnO NPs synthesized using *A. webbiana* was evaluated according to their zone of inhibition and the results were compared with the activity of the standard antimicrobial agent.

4. CONCLUSION

This study has demonstrated that ZnO NPs synthesis was initially identified by dark brown colour and the surface plasmon resonance was peak positioned at 370 nm. These ZnO NPs showed potent antimicrobial activity against oral pathogens assuring its effective therapeutic application in several infectious oral diseases.

CONSENT

It is not applicable.

ETHICAL APPROVAL

It is not applicable

ACKNOWLEDGEMENT

This research was done under the supervision of the department of research of saveetha dental college and hospitals. We thank our colleagues who provided insight and expertise that greatly assisted the research. The present project was supported by Saveetha institute of medical and technical sciences. Saveetha dental college and hospitals, saveetha university and pavithra harvesters.

COMPETING INTERESTS

Authors have declared that no competing interests exist.

REFERENCES

1. Khan ST, Musarrat J, Al-Khedhairy AA. Countering drug resistance, infectious diseases, and sepsis using metal and metal oxides nanoparticles: Current status [Internet]. Colloids and Surfaces B: Biointerfaces. 2016;146:70–83.

Available:http://dx.doi.org/10.1016/j.colsurf b.2016.05.046

- Rajeshkumar S, Bharath LV. Mechanism of plant-mediated synthesis of silver nanoparticles – A review on biomolecules involved, characterisation and antibacterial activity [Internet]. Chemico-Biological Interactions. 2017;273:219–27. Available:http://dx.doi.org/10.1016/j.cbi.201 7.06.019
- 3. Scire S, Palmisano L. Cerium Oxide (CeO2): Synthesis, properties and applications. Elsevier; 2019;402.
- Ahmad A, Mukherjee P, Senapati S, Mandal D, Islam Khan M, Kumar R, et al. Extracellular biosynthesis of silver nanoparticles using the fungus *Fusarium oxysporum* [Internet]. Colloids and Surfaces B: Biointerfaces. 2003;28:313–8. Available: http://dx.doi.org/10.1016/s0927-7765(02)00174-1
- 5. Hernández-Ramírez A, Medina-Ramírez I. Photocatalytic semiconductors: Synthesis, Characterization, and Environmental Applications. Springer. 2014;289.
- 6. Ponnanikajamideen M, Rajeshkumar S, Vanaja M, Annadurai G. *In vivo* type 2 diabetes and wound-healing effects of antioxidant gold nanoparticles synthesized using the insulin plant *Chamaecostus cuspidatus* in Albino Rats [Internet]. Canadian Journal of Diabetes. 2019;43: 82–9.e6.

Available:http://dx.doi.org/10.1016/j.jcjd.20 18.05.006

- 7. Fedlheim DL, Foss CA. Metal nanoparticles: Synthesis, characterization, and applications. CRC Press. 2001;352.
- 8. Rai M, Posten C. Green biosynthesis of nanoparticles: Mechanisms and applications. CABI. 2013;248.
- 9. Vijayakumar S, Vinoj G, Malaikozhundan B, Shanthi S, Vaseeharan B. *Plectranthus amboinicus* leaf extract mediated synthesis of zinc oxide nanoparticles and its control

of methicillin resistant *Staphylococcus aureus* biofilm and blood sucking mosquito larvae. Spectrochim Acta A Mol Biomol Spectrosc. 2015;137:886–91.

- Ramamurthy J, Head A, Department of 10. periodontics, saveetha dental college and hospitals, saveetha institute of medical and technical sciences (simats), saveetha university, et al. green synthesis of copper oxide nanoparticles using aqueous extract ocimum sanctum and analysis of of antimicrobial, anti-inflammatory and cvtotoxic activity of ocimum sanctum copper oxide nanoparticles - An In vitro study [Internet]. International Journal of Dentistry and Oral Science. 2021;2848-52. Available: http://dx.doi.org/10.19070/2377-8075-21000578
- S SK, Satheesha KS. In-Vitro Antibacterial Activity of Black Tea (*Camellia sinensis*) Mediated Zinc Oxide Nanoparticles against Oral Pathogens [Internet]. Bioscience Biotechnology Research Communications. 2020;13:2077–80. Available:http://dx.doi.org/10.21786/bbrc/1 3.4/66
- 12. Mandal S, Professor A, Department of Anatomy, Medical College, Kolkata, Bengal W, et al. Unravelling the mystery behind successful caudal-epidural block [Internet]. International Journal of Anatomy and Research. 2017;5:4492–9. Available: http://dx.doi.org/10.16965/ijar.2017.382
- Rajeshkumar S, Sherif MH, Malarkodi C, Ponnanikajamideen M, Arasu MV, Al-Dhabi NA, et al. Cytotoxicity behaviour of response surface model optimized gold nanoparticles by utilizing fucoidan extracted from padina tetrastromatica [Internet]. Journal of Molecular Structure. 2021;1228:129440. Available:http://dx.doi.org/10.1016/j.molstr uc.2020.129440
- Ganta SSL, Jeevitha M, Preetha S, Rajeshkumar S. Anti-inflammatory activity of dried ginger mediated iron nanoparticles [Internet]. Journal of Pharmaceutical Research International. 2020;14–9. Available:http://dx.doi.org/10.9734/jpri/202 0/v32i2830866
- 15. Nasim I, Kamath K, Rajeshkumar S. Evaluation of the re-mineralization capacity of a gold nanoparticle-based dental varnish: An *In vitro* study [Internet]. Journal of Conservative Dentistry. 2020;23:390. Available:http://dx.doi.org/10.4103/jcd.jcd_ 315_20

- Ramesh A, Varghese S, Jayakumar ND, Malaiappan S. Comparative estimation of sulfiredoxin levels between chronic periodontitis and healthy patients - A casecontrol study. J Periodontol. 2018;89(10):1241–8.
- Paramasivam A, Priyadharsini JV, Raghunandhakumar S, Elumalai P. A novel COVID-19 and its effects on cardiovascular disease. Hypertens Res. 2020;43(7):729–30.
- S G, T G, K V, Faleh A A, Sukumaran A, P N S. Development of 3D scaffolds using nanochitosan/silk-fibroin/hyaluronic acid biomaterials for tissue engineering applications. Int J Biol Macromol. 2018;120(Pt A):876–85.
- Jayaseelan VP, Arumugam P. Dissecting the theranostic potential of exosomes in autoimmune disorders [Internet]. Cellular & Molecular Immunology. 2019;16:935–6. Available:http://dx.doi.org/10.1038/s41423-019-0310-5
- 20. Del Fabbro M, Karanxha L, Panda S, Bucchi C, Nadathur Doraiswamy J, Sankari M, et al. Autologous platelet concentrates for treating periodontal infrabony defects. Cochrane Database Syst Rev. 2018;11:CD011423.
- 21. Paramasivam A, Vijayashree Priyadharsini J. MitomiRs: new emerging microRNAs in mitochondrial dysfunction and cardiovascular disease. Hypertens Res. 2020;43(8):851–3.
- 22. Vellappally S, Al Kheraif AA, Divakar DD, Basavarajappa S, Anil S, Fouad H. Tooth implant prosthesis using ultra low power and low cost crystalline carbon bio-tooth sensor with hybridized data acquisition algorithm [Internet]. Computer Communications. 2019;148:176–84. Available:http://dx.doi.org/10.1016/j.comco m.2019.09.020
- 23. Vellappally S, Al Kheraif AA, Anil S, Assery MK, Kumar KA, Divakar DD. Analyzing Relationship between Patient and Doctor in Public Dental Health using Particle Memetic Multivariable Logistic Regression Analysis Approach (MLRA2). J Med Syst. 2018;42(10):183.
- 24. Varghese SS, Ramesh A, Veeraiyan DN. Blended module-based teaching in biostatistics and research methodology: A retrospective study with postgraduate dental students. J Dent Educ. 2019;83 (4):445–50.
- 25. Venkatesan J, Singh S, Anil S, Kim S-K,

Shim M. Preparation, Characterization and Biological Applications of Biosynthesized Silver Nanoparticles with Chitosan-Fucoidan Coating [Internet]. Molecules. 2018; 23:1429.

Available:http://dx.doi.org/10.3390/molecul es23061429

- Alsubait SA, Al Ajlan R, Mitwalli H, Aburaisi N, Mahmood A, Muthurangan M, et al. Cytotoxicity of Different Concentrations of Three Root Canal Sealers on Human Mesenchymal Stem Cells. Biomolecules [Internet]. 2018;8(3). Available:http://dx.doi.org/10.3390/biom80 30068
- 27. Venkatesan J, Rekha PD, Anil S, Bhatnagar I, Sudha PN, Dechsakulwatana C, et al. Hydroxyapatite from Cuttlefish Bone: Isolation, Characterizations, and Applications [Internet]. Biotechnology and Bioprocess Engineering. 2018;23:383–93. Available:http://dx.doi.org/10.1007/s12257-018-0169-9
- 28. Vellappally S, Al Kheraif AA, Anil S, Wahba AA. IoT medical tooth mounted sensor for monitoring teeth and food level using bacterial optimization along with adaptive deep learning neural network [Internet]. Measurement. 2019;135:672–7. Available:http://dx.doi.org/10.1016/j.measu rement.2018.11.078
- 29. PradeepKumar AR, Shemesh H. Nivedhitha MS, Mohamed Jubair Hashir M, Arockiam S, Maheswari TNU, et al. Diagnosis of vertical root fractures by cone-beam computed tomography in rootfilled teeth with confirmation by direct visualization: A systematic review and meta-analysis [Internet]. Journal of Endodontics. 2021;47:1198-214. Available:http://dx.doi.org/10.1016/j.joen.2 021.04.022
- RH, Hannah R, Ramani P, Tilakaratne WM, Sukumaran G, Ramasubramanian A, et al. Author response for "Critical appraisal of different triggering pathways for the pathobiology of pemphigus vulgaris—A review" [Internet]; 2021. Available:http://dx.doi.org/10.1111/odi.139 37/v2/response1
- 31. Ezhilarasan D, Lakshmi T, Subha M, Deepak Nallasamy V, Raghunandhakumar S. The ambiguous role of sirtuins in head and neck squamous cell carcinoma. Oral Dis [Internet]; 2021.

Available:http://dx.doi.org/10.1111/odi.137 98

- Sarode SC, Gondivkar S, Sarode GS, Gadbail A, Yuwanati M. Hybrid oral potentially malignant disorder: A neglected fact in oral submucous fibrosis. Oral Oncol. 2021;105390.
- Kavarthapu A, Gurumoorthy K. Linking chronic periodontitis and oral cancer: A review [Internet]. Oral Oncology. 2021;105375. Available:http://dx.doi.org/10.1016/j.oralon cology.2021.105375
- 34. Vellappally S, Al-Kheraif AA, Anil S, Basavarajappa S, Hassanein AS. Maintaining patient oral health by using a xeno-genetic spiking neural network [Internet]. Journal of Ambient Intelligence and Humanized Computing; 2018. Available:http://dx.doi.org/10.1007/s12652-018-1166-8
- Aldhuwayhi S, Mallineni SK, Sakhamuri S, Thakare AA, Mallineni S, Sajja R, et al. Covid-19 Knowledge and Perceptions Among Dental Specialists: A Cross-Sectional Online Questionnaire Survey. Risk Manag Healthc Policy. 2021;14:2851– 61.
- Kelly KL, Lance Kelly K, Coronado E, Zhao LL, Schatz GC. The optical properties of metal nanoparticles: The influence of size, shape, and dielectric environment [Internet]. ChemInform. 2003;34. Available:http://dx.doi.org/10.1002/chin.20 0316243
- Palanivelrajan R, Suja S. Biomimetic synthesis, characterization and evaluation of antioxidant, antimicrobial efficacy of silver nanoparticles using *Andredera cordifolia* leaf extract [Internet]. Asian Journal of Pharmaceutical and Clinical Research. 2017;10:329. Available:http://dx.doi.org/10.22159/ajpcr.2 017.v10i4.16819
- Rajeshkumar S. Phytochemical constituents of fucoidan (Padina tetrastromatica) and its assisted AgNPs for enhanced antibacterial activity [Internet]. IET Nanobiotechnology. 2017;11:292– 9.

Available: http://dx.doi.org/10.1049/ietnbt.2016.0099

39. B M, Mustafa B. Preparation, Characterization and Antimicrobial Properties of Silica Based Nanocoatings [Internet]. Journal of Advanced Chemical Engineering. 2018;08.

Available: http://dx.doi.org/10.4172/2090-4568.1000184

- Daniel AN, Sartoretto SM, Schmidt G, 40. Caparroz-Assef SM. Bersani-Amado CA. Cuman RKN. Anti-inflammatory and antinociceptive activities A of eugenol essential oil in experimental animal models [Internet]. Revista Brasileira de Farmacognosia. 2009;19:212-7. Available: http://dx.doi.org/10.1590/s0102-695x2009000200006
- Mankad M, Patil G, Patel S, Patel D, Patel A. Green synthesis of zinc oxide nanoparticles using Azadirachta indica A. Juss. leaves extract and its antibacterial activity against Xanthomonas orzyae pv. oryzae [Internet]. Annals of Phytomedicine : An International Journal. 2016;5:76–86. Available:http://dx.doi.org/10.21276/ap.201 6.5.2.9
- 42. Barma MD, Kannan SD, Indiran MA, Rajeshkumar S, Pradeep Kumar R. Antibacterial Activity of Mouthwash Incorporated with Silica Nanoparticles against S. aureus, S. mutans, E. faecalis: An in-vitro Study [Internet]. Journal of Pharmaceutical Research International. 2020;25–33.

Available:http://dx.doi.org/10.9734/jpri/202 0/v32i1630646

43. Jeevitha M, Rajeshkumar S. Antimicrobial activity of silver nanoparticles synthesized using marine brown seaweed spatoglossum asperum against oral pathogens [Internet]. Indian Journal of Public Health Research & Development. 2019;10:3568.

Available: http://dx.doi.org/10.5958/0976-5506.2019.04140.8

- 44. Rajeshkumar S, Tharani M, Jeevitha M, Santhoshkumar J. Anticariogenic Activity of Fresh Aloe Vera Gel Mediated Copper Oxide Nanoparticles [Internet]. Indian Journal of Public Health Research & Development. 2019;10:3664. Available: http://dx.doi.org/10.5958/0976-5506.2019.04158.5
- 45. Begum A, Jeevitha M, Preetha S, Rajeshkumar S. Cytotoxicity of Iron

Nanoparticles Synthesized Using Dried Ginger [Internet]. Journal of Pharmaceutical Research International. 2020; 112–8. Available:http://dx.doi.org/10.9734/jpri/202

0/v32i2530829

 Ali SJ, Preetha S, Jeevitha M, Prathap L, S. R. Antifungal activity of selenium nanoparticles extracted from *Capparis decidua* fruit against *Candida albicans* [Internet]. Journal of Evolution of Medical and Dental Sciences. 2020;9:2452– 5.

Available:http://dx.doi.org/10.14260/jemds/ 2020/533

- Devi RS, Shruthi Devi R, Jeevitha M, Preetha S, Rajeshkumar S. Free radical scavenging activity of copper nanoparticles synthesized from dried ginger [Internet]. Journal of Pharmaceutical Research International. 2020;1–7. Available:http://dx.doi.org/10.9734/jpri/202 0/v32i1930703
- 48. Antimicrobial activity of copper nanoparticles biosynthesized using dried ginger [Internet]. International Journal of Pharmaceutical Research. 2020;12. Available:http://dx.doi.org/10.31838/ijpr/20 20.12.04.428
- 49. Trisha S, Jeevitha M, Preetha S, Rajeshkumar S. Green synthesis of copper nanoparticles using turmeric-tulsi extract and its characterization. Plant cell biotechnology and molecular biology. 2020;79–84.
- 50. Free radical scavenging activity of iron nanoparticles synthesized using dried ginger [Internet]. International Journal of Pharmaceutical Research. 2020;12. Available:http://dx.doi.org/10.31838/ijpr/20 20.12.04.442
- 51. Shivapriya Raje Bhonsle A, Jeevitha M, Preetha S. Raieshkumar Anti-S. inflammatory activitv of copper nanoparticles synthesized using dried ginger. Plant cell biotechnology and molecular biology. 2020;1-7.

© 2021 Nivethitha et al.; This is an Open Access article distributed under the terms of the Creative Commons Attribution License (http://creativecommons.org/licenses/by/4.0), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history: The peer review history for this paper can be accessed here: https://www.sdiarticle5.com/review-history/78314