



Abies webbiana Mediated Zinc Oxide Nanoparticles and Its Anti-inflammatory Activity

S. Priyadharshini ^a, M. Jeevitha ^{b*}, S. Rajeshkumar ^c and Selvaraj Jayaraman ^d

^aSaveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai, India.

^b Department of Periodontics, Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai, India.

^c Department of Pharmacology, Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai, India.

^d Department of Biochemistry, Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai, India.

Authors' contributions

This work was carried out in collaboration among all authors. Author SP designed the study, performed the statistical analysis, wrote the protocol, and wrote the first draft manuscript. Authors MJ and SR managed the analyses of the study. Author SJ managed the literature searches. All authors read and approved the final manuscript.

Article Information

DOI: 10.9734/JPRI/2021/v33i62B35174

Open Peer Review History:

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: <https://www.sdiarticle5.com/review-history/78095>

Original Research Article

Received 24 October 2021
Accepted 28 December 2021
Published 29 December 2021

ABSTRACT

Introduction: Green nanoparticle synthesis provides a number of advantages, including being environmentally friendly, taking less time, being less expensive, being more stable, and, most significantly, not requiring the use of harmful chemicals.

Aim: The aim of the present study is to evaluate the anti-inflammatory activity of zinc oxide [ZnO] nanoparticles prepared using *Abies webbiana* extract.

Materials and Methods: In this study, ZnO nanoparticles were characterised using ultraviolet-visible spectroscopy and inhibition of albumin denaturation assay using *A. webbiana* extract.

Results: The biosynthesised ZnO particles exhibited potent anti-inflammatory activity to inhibit COX activity. ZnO nanoparticles can be developed as a novel medicine and can be used as an alternative to commercially available anti-inflammatory agents, thus reducing the major health problems.

*Corresponding author: E-mail: jeevitham.sdc@saveetha.com;

Conclusion: Using *A.webbiana* extract, the findings suggest a cost-effective and environmentally friendly production of ZnO nanoparticles. ZnO nanoparticles mediated by *A. webbiana* showed promising properties. More investigations are required to understand the properties of these nanoparticles, which have a wide range of medical and dental applications.

Keywords: *Abies webbiana*; anti-inflammatory; innovative technology; zinc oxide nanoparticles.

1. INTRODUCTION

Cells of living organisms are typical across 10 µm. However, the parts of the cells are much smaller, with typical size of just 5 nm. The smaller size contributes to the idea of using nanoparticles to spy on cellular machinery without much interference [1]. The driving force behind the development of nanotechnology was to understand the biological processes on the nanoscale level [2]. Nanotechnology deals with the manufacture and application of materials with a size of up to 100 nm. The use of nanoparticles in various fields such as material science, agriculture, food industry, cosmetic, medical has emerged [3].

Zinc is an essential trace element for the human system. Body metabolism is maintained by zinc through hematopoiesis, enzyme regulation, maintaining cell redox balance and DNA and protein synthesis machinery regulation [4]. Zinc oxide nanoparticles exhibit various biomedical applications such as tremendous wound healing, catalytic, bio-imaging, anti-bacterial, anti-inflammatory properties [5]. Zinc oxide nanoparticles act by inhibiting the activation of NF-kB [nuclear factor kappa B cells] in mRNA expression of inflammatory cytokines [6]. Owing to the excellent bio-medical properties of zinc oxide nanoparticles, they are used as potential drug delivery vehicles for standard drugs as it provides synergistic effects for the treatment [7].

Abies webbiana tree most commonly seen in the Himalayan region from Kashmir to Assam states in India also found in neighbouring areas of Nepal, Tibet and Afghanistan. *A. webbiana* is a tall, large, evergreen tree seen normally at an altitude of 2500-4000 m. *A. webbiana* also known as Talispatra in Bengali and Hindi, Talispatram in Sanskrit and Indian Silver Fir in English [8].

Leaves of *A. webbiana* has many medicinal uses. Traditionally leaves of this plant have been used for their medicinal properties namely for their carminative, stomachic, expectorant, decongestant, antiseptic, astringent, antihyperglycemic, female antifertility, febrifuge

and anti-spasmodic functions. In cases of cough, phthisis, asthma, chronic bronchitis and catarrh of the bladder and other pulmonary infections, decoctions of the leaves are given orally. Apart from these functions, in cases of serious ailments like rheumatism, hoarseness, chronic bronchitis leaves of the plant have been used traditionally for its chemotherapeutic efficacies [9].

Crude extracts from *A. webbiana* are reported to have antibacterial, mast cell stabilizing, anxiolytic, anti-tumor, anti-inflammatory, antitussive and central nervous system [CNS] depressant actions. Chemical constituents namely monoterpenes [from essential oil], flavonoids, biflavonoid glycosides, phytosterols and diterpene glycosides [taxol like compounds] were isolated from *A. webbiana* leaf. Pinitol which was isolated from leaves of *A.webbiana* was found to have an anti-inflammatory effect [10,11]. Our team has extensive knowledge and research experience that has translated into high-quality publications [12–31]. The aim of the present study is to evaluate the anti-inflammatory activity of *A. webbiana* mediated zinc oxide nanoparticles.

2. MATERIALS AND METHODS

2.1 Preparation of *Abies webbiana* Extract

1gm of powdered *A.webbiana* extract was mixed with 100 mL of distilled water [Fig. 1]. The solution was boiled under 60-70 degrees celsius in the heating mantle for 10-15 minutes. And the solution was filtered using Whatman No. 1 filter paper. The filtered extract was collected and stored at 4° C for further use.

2.2 Synthesis of ZnO Nanoparticles

20 millimolar [0.574g] of zinc sulphate was dissolved in 60 mL of distilled water. 40 mL of filtered *A.webbiana* extract was added with the metal solution. A total of 100 mL of solution was obtained. Colour changes were observed visually and recorded by photographs. The solution is

kept in a magnetic stirrer or orbital shaker for nanoparticle synthesis.

2.3 Characterization of ZnO Nanoparticles

The synthesized zinc oxide nanoparticles solution was preliminarily characterized using ultraviolet [UV]- visible spectroscopy; 3 mL of the solution is taken in the cuvette and scanned in a double-beam UV-visible spectrophotometer from 300 nm to 700 nm wavelength. The results were recorded for the graphical analysis.

2.4 Preparation of Nanoparticles Powder

The nanoparticles solution is centrifuged using Lark refrigerated centrifuge. The ZnO nanoparticles solution was centrifuged at 8000 rpm for 10 mins and the pellet was collected and washed with distilled water twice. The final purified pellet is collected and dried at 100–150°C for 24 h and finally, the nanoparticles powder was collected and stored in an airtight Eppendorf tube.

2.5 Inhibition of Albumin Denaturation Assay

Bovine serum albumin [BSA] was used as a reagent for the assay. BSA makes up approximately 60% of all proteins in animal serum. It is commonly used in culture, particularly when protein supplementation is necessary and the other components of serum are unwanted. BSA undergoes denaturation on heating and starts expressing antigens associated with Type III hypersensitivity reaction which is related to diseases such as rheumatoid arthritis, glomerulonephritis, serum sickness, and systemic lupus erythematosus. Two milliliters of 1% bovine albumin fraction was mixed with 400 µl of plant crude extract in different concentrations [500–100 µg/mL] and the pH of the reaction mixture was adjusted to 6.8 using 1 N HCl. The reaction mixture was incubated at room temperature for 20 min and then heated at 55°C for 20 min in a water bath. The mixture was cooled to room temperature and the absorbance value was recorded at 660 nm. An equal amount of plant extract was replaced with DMSO for control. Diclofenac sodium in different concentrations was used as standard. The experiment was performed in triplicate.

% Inhibition was calculated using the formulae:

$$\% \text{ Inhibition} = \frac{\text{Control O. D} - \text{sample O. D}}{\text{Control O. D}}$$

3. RESULTS AND DISCUSSION

3.1 Visual Observation

The present study shows the synthesis of Zinc oxide nanoparticles by using *A. webbiana*. Reduction of Zinc sulfate to zinc ion process was observed by colour change through direct visual observation of the solution. At various stages of incubation, the colour changes in the reaction mixture were examined continuously. Color change revealed that the zinc oxide had been converted into ZnO nanoparticles. After incubating for 1 hour, the colour of the solution had changed to brown. After 24 hours of incubation, the colour turned from light brown to dark brown [Figs. 2 and 3]. After 24 hours, no colour change was observed indicating that the creation of Zinc oxide nanoparticles was complete. Bio- based synthesis of ZnO nanoparticles prepared from using amla fruits observed colour change from yellow to dark brown [32]. Similar colour change was observed in the present study.

3.2 UV-visible Spectroscopy

The UV-visible analysis of the ZnO nanoparticles was analyzed in the absorbency range of 250–500 nm. The peak was found to be maximum at 350 nm [Fig. 4]. Reduction of aqueous metal ions with the *A. webbiana* extract indicates the formation and synthesis of the ZnO nanoparticles. ZnO nanoparticles synthesized from Amla fruit showed plasmon resonance at 350nm [32].

3.3 Anti-inflammatory Activity

The anti-inflammatory activity of the *A. webbiana* extract was measured by the inhibition of albumin denaturation assay. The synthesized zinc oxide nanoparticles showed the quality of anti-inflammatory activity in the range of 80–90%, respectively (Fig. 5). The extract showed a greater percentage of inhibition when compared to the standard solution.



Fig. 1. Dried *A. webbiana* powder and 100 mL of distilled water




Fig. 2. ZnO nanoparticles solution




Fig. 3. Visual observation of *A. webbiana* and ZnO nanoparticles




Fig. 4. UV vis spectroscopy of ZnO nanoparticles synthesized using *A. webbiana* recorded as function of time




Fig. 5. The quality of anti-inflammatory activity ZnO nanoparticles synthesized using *A. webbiana* which is compared to the standard substance

Inflammation occurs as a response of our immune system to harmful stimuli which represents pathological conditions. Various chronic diseases are associated with inflammation process e.g., cancer, diabetes, inflammatory bowel disease and rheumatoid arthritis. Several cell types of neutrophils, basophils, eosinophils, and mononuclear cells are involved in the inflammatory process [33–35].

Inflammation can be of two types as either acute or chronic inflammation. Cyclooxygenase [COX] is the key causative factor/ enzyme in the synthesis of prostaglandins, prostacyclins and thromboxanes which are responsible for inflammation, pain, and platelet aggregation [32,36].

Non-steroidal anti-inflammatory drugs and immunosuppressants are currently most widely used in the treatment of acute inflammatory disorders. However there are many undesired side effects compared to the effectiveness of the drugs which deepens the needs and discovery of new anti-inflammatory drugs [37,38].

Some researchers have reported that ZnO nanoparticles exhibit potent anti-inflammatory action by inhibiting COX activity. ZnO nanoparticles extracted from *Polygala tenuifolia* root, exhibited excellent anti-inflammatory activity

by dose-dependently inhibiting the LPS-induced protein expression of COX-2 and iNOS [39].

The most commonly used anti-inflammatory group of drugs includes aspirin, diclofenac, and ibuprofen. The drugs have adverse side effects on the liver and gastrointestinal tract. Based on in-vitro studies, ZnO nanoparticles showed anti-inflammatory activity and can be considered as a potential candidate as an anti-inflammatory agent.

4. CONCLUSION

The present study has demonstrated an eco-friendly and cost-effective synthesis of ZnO nanoparticles using *A.webbiana* extract. ZnO synthesis was identified initially by direct visual observation of colour change to dark brown colour. UV-visible analysis of the ZnO nanoparticles was analyzed in the absorbency range of 250–500 nm. The peak was found to be maximum at 350 nm. The ZnO nanoparticles showed potent anti-inflammatory activity by inhibiting COX. Assuring its effectiveness in the therapeutic application for various diseases. The development of new classes of analgesics and anti-inflammatory drugs from *A. webbiana* is still under further investigation.

DISCLAIMER

The products used for this research are commonly and predominantly used products in

our area of research and country. There is absolutely no conflict of interest between the authors and producers of the products because we do not intend to use these products as an avenue for any litigation but for the advancement of knowledge. Also, the research was not funded by the producing company rather it was funded by the personal efforts of the authors.

ACKNOWLEDGEMENT

The authors sincerely acknowledge the support from Saveetha institute of Medical and Technical sciences [SIMATS] and also the authors would like to thank Saveetha Dental College and Hospitals, Saveetha institute of Medical and Technical sciences [SIMATS], Saveetha University and Auditing solutions, Trichy for providing a platform to carry out this study.

CONSENT

It is not applicable.

ETHICAL APPROVAL

It is not applicable.

COMPETING INTERESTS

Authors have declared that no competing interests exist.

REFERENCES

1. Taton TA, Andrew Taton T. Nanostructures as tailored biological probes [Internet]. Trends in Biotechnology. 2002;20:277–9. Available: [http://dx.doi.org/10.1016/s0167-7799\[02\]01973-x](http://dx.doi.org/10.1016/s0167-7799[02]01973-x)
2. Whitesides GM. The “right” size in nanobiotechnology. Nat Biotechnol. 2003;21[10]:1161–5.
3. Santhoshkumar J, Rajeshkumar S, Venkat Kumar S. Phyto-assisted synthesis, characterization and applications of gold nanoparticles – A review [Internet]. Biochemistry and Biophysics Reports. 2017;11:46–57. Available: <http://dx.doi.org/10.1016/j.bbrep.2017.06.004>
4. Auld DS. Zinc coordination sphere in biochemical zinc sites [Internet]. Zinc Biochemistry, Physiology, and Homeostasis. 2001;85–127. Available from: http://dx.doi.org/10.1007/978-94-017-3728-9_6
5. Yuvakkumar R, Suresh J, Hong SI. Green Synthesis of Zinc Oxide Nanoparticles [Internet]. Advanced Materials Research. 2014;952:137–40. Available: <http://dx.doi.org/10.4028/www.scientific.net/amr.952.137>
6. Kim MH, Seo JH, Kim HM, Jeong HJ. Zinc oxide nanoparticles, a novel candidate for the treatment of allergic inflammatory diseases. Eur J Pharmacol. 2014;738:31–9.
7. Bala N, Saha S, Chakraborty M, Maiti M, Das S, Basu R, et al. Green synthesis of zinc oxide nanoparticles using Hibiscus subdariffa leaf extract: effect of temperature on synthesis, anti-bacterial activity and anti-diabetic activity [Internet]. RSC Advances. 2015;5:4993–5003. Available: <http://dx.doi.org/10.1039/c4ra12784f>
8. Ghosh AK, Sen D, Bhattacharya S. A new alkaloid isolated from *Abies webbiana* leaf. Pharmacognosy Res. 2010;2[3]:186–9.
9. Singh RK, Bhattacharya SK, Acharya SB. Pharmacological activity of *Abies pindrow* [Internet]. Journal of Ethnopharmacology. 2000;73:47–51. Available: [http://dx.doi.org/10.1016/s0378-8741\[00\]00278-6](http://dx.doi.org/10.1016/s0378-8741[00]00278-6)
10. Khare. Indian medicinal plants: An illustrated dictionary. 2007;900.
11. Singh RK, Pandey BL, Tripathi M, Pandey VB. Anti-inflammatory effect of []-pinitol [Internet]. Fitoterapia. 2001;72:168–70. Available: [http://dx.doi.org/10.1016/s0367-326x\[00\]00267-7](http://dx.doi.org/10.1016/s0367-326x[00]00267-7)
12. Ramesh A, Varghese S, Jayakumar ND, Malaiappan S. Comparative estimation of sulfiredoxin levels between chronic periodontitis and healthy patients - A case-control study. J Periodontol. 2018; 89[10]:1241–8.
13. Paramasivam A, Priyadharshini JV, Raghunandhakumar S, Elumalai P. A novel COVID-19 and its effects on cardiovascular disease. Hypertens Res. 2020;43[7]:729–30.
14. SG, TG, KV, Faleh AA, Sukumaran A, PS. Development of 3D scaffolds using nanochitosan/silk-fibroin/hyaluronic acid biomaterials for tissue engineering applications. Int J Biol Macromol. 2018;120[Pt A]:876–85.
15. Del Fabbro M, Karanxha L, Panda S, Bucchi C, Nadathur Doraiswamy J,

- Sankari M, et al. Autologous platelet concentrates for treating periodontal infrabony defects. *Cochrane Database Syst Rev.* 2018;11:CD011423.
16. Paramasivam A, Vijayashree Priyadharsini J. MitomiRs: new emerging microRNAs in mitochondrial dysfunction and cardiovascular disease. *Hypertens Res.* 2020;43[8]:851–3.
 17. Jayaseelan VP, Arumugam P. Dissecting the theranostic potential of exosomes in autoimmune disorders. *Cell Mol Immunol.* 2019;16[12]:935–6.
 18. Vellappally S, Al Kheraif AA, Divakar DD, Basavarajappa S, Anil S, Fouad H. Tooth implant prosthesis using ultra low power and low cost crystalline carbon bio-tooth sensor with hybridized data acquisition algorithm [Internet]. *Computer Communications.* 2019;148:176–84. Available:<http://dx.doi.org/10.1016/j.comcom.2019.09.020>
 19. Vellappally S, Al Kheraif AA, Anil S, Assery MK, Kumar KA, Divakar DD. Analyzing relationship between patient and doctor in public dental health using particle memetic multivariable logistic regression analysis approach [MLRA2]. *J Med Syst.* 2018;42[10]:183.
 20. Varghese SS, Ramesh A, Veeraiyan DN. Blended module-based teaching in biostatistics and research methodology: a retrospective study with postgraduate dental students [Internet]. *Journal of Dental Education.* 2019;83:445–50. Available: <http://dx.doi.org/10.21815/jde.019.054>
 21. Venkatesan J, Singh S, Anil S, Kim S-K, Shim M. Preparation, characterization and biological applications of biosynthesized silver nanoparticles with chitosan-fucoidan coating [Internet]. *Molecules.* 2018; 23:1429. Available:<http://dx.doi.org/10.3390/molecules23061429>
 22. Alsubait S, Al Ajlan R, Mitwalli H, Aburaisi N, Mahmood A, Muthurangan M, et al. Cytotoxicity of different concentrations of three root canal sealers on human mesenchymal stem cells [Internet]. *Biomolecules.* 2018;8:68. Available:<http://dx.doi.org/10.3390/biom8030068>
 23. Venkatesan J, Rekha PD, Anil S, Bhatnagar I, Sudha PN, Dechsakulwatana C, et al. Hydroxyapatite from cuttlefish bone: Isolation, characterizations, and applications [Internet]. *Biotechnology and Bioprocess Engineering.* 2018;23:383–93. Available:<http://dx.doi.org/10.1007/s12257-018-0169-9>
 24. Vellappally S, Al Kheraif AA, Anil S, Wahba AA. IoT medical tooth mounted sensor for monitoring teeth and food level using bacterial optimization along with adaptive deep learning neural network [Internet]. *Measurement.* 2019;135:672–7. Available:<http://dx.doi.org/10.1016/j.measurement.2018.11.078>
 25. PradeepKumar AR, Shemesh H, Nivedhitha MS, Hashir MMJ, Arockiam S, Uma Maheswari TN, et al. Diagnosis of Vertical Root Fractures by Cone-beam Computed Tomography in Root-filled Teeth with Confirmation by Direct Visualization: A Systematic Review and Meta-Analysis. *J Endod.* 2021;47[8]:1198–214.
 26. RH, Ramani P, Tilakaratne WM, Sukumaran G, Ramasubramanian A, Krishnan RP. Critical appraisal of different triggering pathways for the pathobiology of pemphigus vulgaris-A review. *Oral Dis* [Internet]; 2021. Available:<http://dx.doi.org/10.1111/odi.13937>
 27. Ezhilarasan D, Lakshmi T, Subha M, Deepak Nallasamy V, Raghunandhakumar S. The ambiguous role of sirtuins in head and neck squamous cell carcinoma. *Oral Dis* [Internet]; 2021. Available:<http://dx.doi.org/10.1111/odi.13798>
 28. Sarode SC, Gondivkar S, Sarode GS, Gadbail A, Yuwanati M. Hybrid oral potentially malignant disorder: A neglected fact in oral submucous fibrosis. *Oral Oncol.* 2021;105390.
 29. Kavarthapu A, Gurumoorthy K. Linking chronic periodontitis and oral cancer: A review. *Oral Oncol.* 2021;105375.
 30. Vellappally S, Al-Kheraif AA, Anil S, Basavarajappa S, Hassanein AS. Maintaining patient oral health by using a xeno-genetic spiking neural network [Internet]. *Journal of Ambient Intelligence and Humanized Computing;* 2018. Available:<http://dx.doi.org/10.1007/s12652-018-1166-8>
 31. Aldhuwayhi S, Mallineni SK, Sakhamuri S, Thakare AA, Mallineni S, Sajja R, et al. COVID-19 Knowledge and Perceptions Among Dental Specialists: A Cross-Sectional Online Questionnaire Survey.

- Risk Manag Healthc Policy. 2021;14:2851–61.
32. MS, Srinisha M, Rajeshkumar S, Lakshmi T, Roy A. Amla fruit mediated synthesis of zinc oxide nanoparticles and its antifungal activity [Internet]. International Journal of Research in Pharmaceutical Sciences. 2019;10:2826–9. Available: <http://dx.doi.org/10.26452/ijrps.v10i4.1554>
 33. Siracusa MC, Kim BS, Spergel JM, Artis D. Basophils and allergic inflammation [Internet]. Journal of Allergy and Clinical Immunology. 2013;132:789–801. Available: <http://dx.doi.org/10.1016/j.jaci.2013.07.046>
 34. Leliefeld PHC, Wessels CM, Leenen LPH, Koenderman L, Pillay J. The role of neutrophils in immune dysfunction during severe inflammation. Crit Care. 2016; 20:73.
 35. Geering B, Stoeckle C, Conus S, Simon H-U. Living and dying for inflammation: neutrophils, eosinophils, basophils. Trends Immunol. 2013;34[8]:398–409.
 36. Pilotto A, Sancarolo D, Addante F, Scarcelli C, Franceschi M. Non-steroidal anti-inflammatory drug use in the elderly. Surg Oncol. 2010;19[3]:167–72.
 37. Sostres C, Gargallo CJ, Arroyo MT, Lanas A. Adverse effects of non-steroidal anti-inflammatory drugs [NSAIDs, aspirin and coxibs] on upper gastrointestinal tract. Best Pract Res Clin Gastroenterol. 2010; 24[2]:121–32.
 38. Oray M, Abu Samra K, Ebrahimiadib N, Meese H, Foster CS. Long-term side effects of glucocorticoids. Expert Opin Drug Saf. 2016;15[4]:457–65.
 39. Nagajyothi PC, Cha SJ, Yang IJ, Sreekanth TVM, Kim KJ, Shin HM. Antioxidant and anti-inflammatory activities of zinc oxide nanoparticles synthesized using Polygala tenuifolia root extract [Internet]. Journal of Photochemistry and Photobiology B: Biology. 2015;146:10–7. Available:<http://dx.doi.org/10.1016/j.jphoto biol.2015.02.008>

© 2021 Priyadharshini et al.; This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history:

The peer review history for this paper can be accessed here:
<https://www.sdiarticle5.com/review-history/78095>